



#Rives - #creativitàdecorativa  
www.rives.it



Azienda certificata  
UNI EN ISO 9001 - 14001

## Rossocamin

Technical Data Sheet No. 123 - Revision 0 of 03/15/2013

### Features and fields of application:

ROSSO CAMIN is a microporous acrylic water-based paint, specifically formulated for fireplaces, formulated with ultra-pure color oxides and high-quality resins. These paints provide a pleasing aesthetic, excellent washability, high coverage, and exceptional durability for both interior and exterior applications. It can be applied as a top coat on a variety of substrates, including concrete, plaster, gypsum, drywall, wood, and more.

### Substrate preparation and application:

Thoroughly dust the surface to be treated and remove any loose particles.

Mix the product thoroughly, dilute it with 30-35% pure water by volume, stir thoroughly, and apply using a brush or roller. After 3-4 hours, apply a second coat, diluting the product 25-30% by volume with pure water.



### USEFUL WARNINGS

- Do not apply at temperatures below +5°C, above +30°C, or with humidity above 75%.
- Use water to clean tools.
- For information on proper disposal, storage, and handling of the product, please consult the relevant safety data sheet.
- The product should be used preferably within two years from the production date if stored in the original, unopened containers and at appropriate temperatures.



#Rives - #creativitàdecorativa  
www.rives.it



Azienda certificata  
UNI EN ISO 9001 - 14001

## Rossocamin

Technical Data Sheet No. 123 - Revision 0 of 03/15/2013

<b>Binder nature</b>	Acrylic emulsion
<b>Specific gravity at 20°C</b>	1620 g/l +/- 50
<b>Viscosity: Brookfield, 6 rpm, speed 20, 20°C</b>	cP 38500
<b>Flash point</b>	Non-flammable
<b>Dry film appearance</b>	Matt
<b>Apply with</b>	Brush, roller
<b>Color</b>	Red oxide
<b>Coverage (kg/m<sup>2</sup>)</b>	3-4 m <sup>2</sup> /L in two coats
<b>Packaging (kg)</b>	L 0.375
<b>Drying</b>	<b>Touch dry:</b> 2 hours at 20°C
	<b>Overcoating:</b> 12 hours at 20°C
	<b>Through drying:</b> 24 hours at 20°C
<b>Dilution</b>	25-35% with pure water
<b>Tool Cleaning</b>	Immediately after use with water
<b>Storage</b>	In a cool, dry place

### Specifications

Application by roller, brush, or airless sprayer of two coats of universal zinc-adherent enamel on pre-prepared substrates.