



#Rives - #creativitàdecorativa
www.rives.it



Azienda certificata
UNI EN ISO 9001 - 14001

Rasoplast

Technical Data Sheet No. 140 - Revision 2 of 28/09/2026

RASOPLAST

Smoothing paste.

Characteristics and areas of use:

RASOPLAST is a thick cement-based smoothing compound with excellent adhesive and filling properties, excellent flowability, and ease of application.

RASOPLAST is suitable for smoothing and leveling uneven surfaces such as scratched, gritty, rolled, and textured surfaces, as well as other types of substrates such as tiles, bricks, natural stone, concrete, and both smooth and porous surfaces.



Substrate preparation:

Remove any dirt or loose paint from the substrate by mechanically removing any loose or flaking particles.

Wash with water to remove any dusty residue that could prevent proper adhesion.

Add 30% white or gray cement and mix until a homogeneous paste is obtained. Apply a first coat of RASOPLAST with a stainless steel trowel. After 12 hours, at 20°C or on a dry surface, apply a second coat of RASOPLAST, working to smooth out any cracks or unevenness.

USEFUL WARNINGS

- To avoid film formation defects, do not apply in direct sunlight or wind, or at temperatures below +5°C.
- Use water to clean tools.
- For information on proper disposal, storage, and handling of the product, please consult the relevant safety data sheet.
- The product should be used preferably within two years of the production date if stored in the original, unopened containers and at suitable temperatures.



#Rives - #creativitàdecorativa
www.rives.it



Azienda certificata
UNI EN ISO 9001 - 14001

Rasoplast

Technical Data Sheet No. 140 - Revision 2 of 28/09/2026

Binder type	styrene-acrylic emulsion
Specific gravity at 20°C	1.5 to 1.6 kg/L
Viscosity: Brookfield, 6 rpm, speed 20, 20°C	60,000 cP
Dry film appearance	matte
Apply with	stainless steel trowel
Color	white
Coverage (kg/m²)	0.8–1.2 kg/m² (two coats)
Packaging (kg)	20 kg
Drying	Touch dry: 4 hours at 20°C
	Overcoating: 24 hours at 20°C
	Through drying: 24 hours at 20°C
Dilution	30% white cement added
Tool Cleaning	Immediately after use with water
Storage	In a cool, dry place